



57640 North Eleventh Street  
Calumet, MI 49913  
Ph. (906) 337-3018  
Fax (906) 337-2930  
rel@relinc.com  
www.relinc.com

## REL TAM Panel - Single (Part Number: 250-00104)



### Certification

REL certifies that REL TAM Panels are Hexavalent Chromium free.

Compliances met by REL TAM Panel plating: RoHS, REACH, WEEE, ELV, and Proposition 65.

Pratt & Whitney Approved TAM 146040-1 (Mirror/Polished Finish).

REL, Inc. is an officially approved P&W Source Manufacturer. REL, Inc. certifies that the Fluorescent Penetrant Inspection REL TAM Panel meets the requirements as stated in **TAM 146040-1, ASTM E1417, MIL-STD-6866, TO 33B-1-1, NAVAIR 01-1A-16-1, TM 1-1500-335-23, Rolls-Royce, and GE Aviation Process Specification P3TF47**. The REL TAM Panel has been manufactured and tested in accordance with the REL, Inc. procedure RWI-1105.

REL TAM Panel and Documentation includes:

1. REL Tam Panel in Tool Control System
2. Panel Certificate of Conformance (Sealed) *\*this document*
3. Penetrant System Monitoring Panel Documentation
  - a. Serialized crack size certification document, including
  - b. 1:1 Picture

REL TAM Panel Cleaning Procedure:

1. **Ultrasonically** clean in 98% methanol for 15 minutes,
  - a. Alternate Cleaning Methods:
    - i. Ultrasonically clean in Acetone
    - ii. Ultrasonically clean in Isopropyl Alcohol

**\*NOTE: Do NOT use Oxidizing Chemicals to Clean panel\***
2. 15 minutes air dry,
3. Verify cleanliness:
  - a. Use a LED UV-A lamp Certified to ASTM E3022. (See illustrations on 'ASTM E3022 Certified Inspection Lamps'. REL, Inc. document included for lamps approved for this purpose.)
  - b. Inspect REL TAM Panel (5 places) at the intensity level of 3000 microwatts per centimeter squared to verify no residual fluorescent penetrant exists on the surface.

REL TAM Panel storage:

1. Store in dry packaging, or
2. Store in Acetone

REL TAM Panel Serial Number: 290714-145

Date of Certification: September 14, 2026

Certified by:                     RWB                      
Inspector

REL TAM Panel Processing Procedure:

Type 1 (Fluorescent Dye), Method D (Post-Emulsifiable, Hydrophilic), Form a (Dry Powder), Level 4 (Ultra-high sensitivity)

1. Clean panel to specified "REL TAM Panel Cleaning Procedure"
2. Apply Fluorescent Penetrant by brush
  - a. Magnaflux Zyglo ZL-37 Level 4, Post-Emulsifiable, Fluorescent Penetrant
3. Penetrant Dwell: 20 minutes @ ambient temperature (50-90°F)
4. Penetrant Rinse: 1 minute maximum wash/rinse 90°F @ 20psi, 18" from part
5. Dip application Emulsifier/Remover:
  - a. Magnaflux Zyglo ZR-10E Hydrophilic Emulsifier (Maximum 20% solution)
6. Emulsifier Dwell: 1 minute maximum in 20% ZR-10E Emulsifier solution
7. Emulsifier Wash/Rinse: 1 minute maximum wash/rinse 90°F @ 20psi, 18" from part
8. Oven Dry: Dry for 5 minutes @ 60°C (140°F)
9. Apply Dry Developer:
  - a. Place panel in Developer Chamber
  - b. Magnaflux Zyglo ZP-4D Dry Powder Developer (formerly ZP-4B)
  - c. Agitate air in chamber to ensure complete coverage
10. Developer Dwell: 10 minutes
11. Remove excess Developer
  - a. Air spray @ 5psi
12. Inspect, Measure, & Document Panel
  - a. Pratt & Whitney TAM146040
  - b. ASTM E1417
13. Lab environmental conditions
  - a. Temperature 73 F
  - b. Humidity 40%

NIST Traceable Process Instrumentation:

1. UV-A & White Light Meter
2. Mini alarm timer/stopwatch
3. Water pressure gauge
4. Water temperature gauge
5. Refractometer
6. Thermocouple
7. Dryer controller
8. Air pressure gauge
9. Keyence IM-8010 Microscope
10. UV-A inspection lamps
11. All instruments used during panel processing procedure are NIST Traceable



# Penetrant System Monitoring Panel Documentation

SN# 290714-145

| Crack Position                                      | A             | B             | C             | D             | E             |
|-----------------------------------------------------|---------------|---------------|---------------|---------------|---------------|
| Photo of Defect<br>Magnification Factor:<br>1 : 3.5 |               |               |               |               |               |
| Measured Size (Inch)                                | 0.031         | 0.061         | 0.084         | 0.148         | 0.207         |
| Specification (Inch)                                | 0.015 - 0.031 | 0.046 - 0.062 | 0.075 - 0.093 | 0.125 - 0.171 | 0.180 - 0.250 |
| Measured Size (mm)                                  | 0.79          | 1.55          | 2.13          | 3.76          | 5.26          |
| Specification (mm)                                  | 0.38 - 0.79   | 1.17 - 1.57   | 1.91 - 2.36   | 3.18 - 4.34   | 4.57 - 6.35   |

|             |                 |               |
|-------------|-----------------|---------------|
| Crack Depth | .0025" ± .0001" | 63 µm ± 2.5µm |
|-------------|-----------------|---------------|

This panel has been tested to conform to all requirements of:  
TAM146040-1

Measured with Keyence IM  
8010  
Calibration No. RM4133305C

Inspector: RWB

Date of Certification: 9/14/26

This panel does not contain hexavalent chromium.



This photo is actual size. (1:1)